Technical data Standard:GB18173.1-2012

No	ITEM		FS2
1	Tension N/cm	Normal temperature ≥	60
		60°C ≥	30
2	Pull lengthening,%	Normal temperature ≥	400
		-20°C	300
3	Break tension,N		50
4	Water impermeability,30min,0.3Mpa		No leaking
5	Cold bending,°C ≤		-20
6	Heating elongation,mm	elongation ≤	2
		shrinkage ≤	4
7	Hot air ageing (80°C×168h)	holding of tension strength at break % ≥	80
		holding of pull lengthening at break % ≥	70
8	Alkali-proof[10%Ca（$OH)_2$ normal temperature ×168h]	holding of tension strength at break % ≥	80
		holding of pull lengthening at break % ≥	80

Waterproof membrane suitable for shower floors and walls, for horizontal or vertical installation.

Onder voorbehoud van wijzigingen en drukfouten
Sous réserve de modifications et d'erreurs d'impression
Subject to changes and printing errors