

Technical data Standard:GB18173.1-2012

No	ITEM		FS2
1	Tension N/cm	Normal temperature $\geq$	60
		60°C $\geq$	30
2	Pull lengthening,%	Normal temperature $\geq$	400
		-20°C	300
3	Break tension,N		50
4	Water impermeability,30min,0.3Mpa		No leaking
5	Cold bending,°C $\leq$		-20
6	Heating elongation,mm	elongation $\leq$	2
		shrinkage $\leq$	4
7	Hot air ageing (80°C×168h)	holding of tension strength at break % $\geq$	80
		holding of pull lengthening at break % $\geq$	70
8	Alkali-proof[10%Ca (OH) ₂ normal temperature ×168h]	holding of tension strength at break % $\geq$	80
		holding of pull lengthening at break % $\geq$	80

Waterproof membrane suitable for shower floors and walls, for horizontal or vertical installation.